



Product Data

Turbinol X

Premium Turbine Lubricant

Description

The BP Turbinol X turbine oil range of lubricants is based upon premium quality mineral oils enhanced with rust and oxidation inhibitors to give maximum protection at high temperatures.

Application

Turbinol X grades are recommended for industrial gas turbines where the lubricant is likely to be exposed to very high localised temperatures. They are also suitable for the lubrication of steam turbines and Combined Cycle generating systems where the steam and gas turbines share a common oil supply.

Turbinol X grades possess superior air release performance, good resistance to foaming and excellent water separation properties.

The Turbinol X range is fully compatible with nitrile, silicone and fluropolymer seal materials.

Turbinol X grades meet the requirements of:

British Standard BS 489

DIN 51515-1 and -2

GEK 32568F (ISO 32)

GEK 107395A (ISO 32)

Alstom HTDG 90 117 (formerly ABB) (ISO 32 and 46)

Siemens TLV 9013 04 and 05 (ISO 32 and 46)

Advantages

- Superior resistance to oxidation & thermal degradation provides a very long life lubricant because of low deposit / lacquer formation.
- Superior air release properties mean they meet the requirements of all turbine manufacturers.
- Excellent water separation and corrosion inhibition mean reduced down time through prolonged lubricant life and increased equipment reliability.
- Suitable for the lubrication of both gas and steam turbines makes them suitable for combined cycle generating stations.

Typical Characteristics

Name	Method	Units	Turbinol X 32	Turbinol X 46	Turbinol X 68
ISO Viscosity Grade	-	-	32	46	68
Relative Density at 15°C	ISO 12185, ASTM D4052	-	0.86	0.86	0.87
Kinematic Viscosity at 40°C	ISO 3104, ASTM D445	mm ² /s	32	46	68
Kinematic Viscosity at 100°C	ISO 3104, ASTM D445	mm ² /s	5.7	7.1	9.5
Viscosity Index	ISO 2909, ASTM D2270	-	>100	>100	>100
Foam Sequence I (tendency/stability)	ISO 6247, ASTM D892	ml	10/0	10/0	10/0
Air Release at 50°C	ISO 9120, ASTM D3427	minutes	2	2	3
Demulsification	IP 19	seconds	60	60	90
Pour Point	ISO 3016, ASTM D97	°C/ °F	-15/ 5	-15/ 5	-12/ 10
Flash Point, COC	ISO 2592, ASTM D92	°C/ °F	222/ 432	234/ 453	234/ 453
Total Acid Number (Potentiometric)	ISO 6619, ASTM D664	mg KOH/g	0.05	0.05	0.05
Rust Test (24hrs synthetic sea water)	ISO 7210, ASTM D665B	-	Pass	Pass	Pass
RPVOT	ASTM D2272	minutes	>1000	>1000	>1000
Copper Corrosion (3hrs at 100°C)	ISO 2160, ASTM D130	-	1 max	1 max	1 max
TOST Test, to 2 mg KOH/g	ASTM D943	hours	>10000	>10000	>10000

Subject to usual manufacturing instructions.

Turbinol X
11 Oct 2011
BP, the BP logo and related marks are trademarks of BP p.l.c., used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Enter Address, Enter Telephone No.

www.castrol.com/industrial