

## Castrol Braycote 803 RP

Perfluoroether Grease, Rust Inhibited  
Wide Temperature, Low Volatility

### Description

Castrol Braycote® 803RP is a smooth, buttery, off-white NLGI#2 grease, based on perfluoropolyether oil (Castrol Brayco® 812) and thickened with a tetrafluoroethylene gelling agent. It contains a rust and corrosion inhibitor for ferric component protection. Castrol Braycote® 803RP is thermally stable in air, vacuum, strong acids and oxidizers. Castrol Fluoroclean™ X 100 or Castrol Fluoroclean™ HE can be used to clean this product. Refer to the data sheets for information regarding these products.

### Application

Castrol Braycote® 803RP was developed for use in applications in which long- term exposure to high temperature or hard vacuum is expected. This product is fully compatible for use in direct or indirect contact with Liquid and Gaseous Oxygen (LOX/GOX). Castrol Braycote® 803RP is stable with exposure to strong acids and oxidizers. Perfluorinated greases, in general, exhibit excellent shelf lives due to their intrinsic inertness.

### Typical Characteristics

TEST (ASTM)	DESCRIPTION	RESULT
D 1403	Penetration @ 25°C (77°F), mm <sup>-1</sup>	
	Unworked	287
	Worked, 60 strokes	288
D 2595	Evaporation Loss, % wt 22 hrs @ 204°C (400°F)	0.29
FTM 321	Oil Separation, % wt 30 hrs @ 204°C (400°F)	8.83
FTM 5309	Copper Strip Corrosion 22 hrs @ 99°C (210°F)	1b
D 2266	Four-Ball Wear-Test, AWSD, mm 1200 rpm, 40 kgf, 1 hr, 75°C (167°F)	0.75
D 2596	Four-Ball Extreme-Pressure Test No Weld Point, kgf	800
D 3336	High Temperature Bearing Performance 204°C (400°F), 10,000 rpm, hrs	2000+
D 1478	Low-Temperature Torque, g.cm @ -54°C (-65°F)	
	Starting	1800
	Running, 1 hr	1050
	@ -62°C (-80°F)	
	Starting	2220
	Running, 1 hr	1295
E 595	Vacuum Stability Test	
	125°C (257°F), 24 hrs, 10 <sup>-6</sup> torr	
	Total Weight Loss, % wt	0.1
	Volatile Condensable Materials, % wt	0
D 2512	LOX Impact Sensitivity 1100 mm, 20 drops	Pass

**Base Oil Information:**

	Pounds per gallon @ 16°C (60°F)	15.71
D 445	Kinematic Viscosity, cSt	
	@ 20°C (68°F)	434
	@ 40°C (104°F)	187
	@ 100°C (212°F)	33
D 2270	Viscosity Index	224
Knudsen	Vapor Pressure, torr	
	@ 20°C (68°F)	$<1 \times 10^{-10}$
	@ 100°C (212°F)	$<1 \times 10^{-7}$
D 97	Pour Point, °C(°F)	$<-60 (-75)$

## Additional Information

### Temperature Range

Below -62°C to above 260°C (below -80°F to above 499°F). Lower temperature operation below -62°C (-80°F) is possible where adequate torque is available.

### Compatibility

Castrol Braycote® 803RP is compatible with all commonly used construction materials including metals, plastics and elastomers. Lewis Acids, such as aluminum chloride, can adversely affect any PFPE grease at elevated temperature. Newly exposed rubbing surfaces of aluminum, magnesium or titanium at elevated temperatures may react with Castrol Braycote® 803RP under certain conditions. Such systems should be thoroughly evaluated. Surfaces must be well cleaned of organic rust inhibitors prior to grease application to ensure proper lubrication.

### Packaging

Castrol Braycote® 803RP is available in 2 ounce (AVDP) disposable plastic syringes and 1 pound plastic jars.

Castrol, Braycote, and the Castrol logo are trademarks of Castrol Limited, used under license

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet.

It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial North America Inc. 150 West Warrenville Road, 605 3E Naperville, IL 60563  
Tel: (877) 641 1600 Fax: (877) 648 9801

**[www.castrol.com/industrial](http://www.castrol.com/industrial)**

Castrol Braycote 803 RP